

calculation in accordance to EN 410

032

Glazing from outside to inside 26.00 mm

pane1	substrate	Guardian Float Glass ExtraClear, 6.00 mm
	coating on pos.2	Guardian SunGuard HS SuperNeutral 62/34
spacer/gas1		16 mm / air 10%, argon 90%
pane2	substrate	Guardian Float Glass ExtraClear, 4.00 mm

Results

UV :		
transmittance [%] :		$\tau_{UV} = 20,5$
light :		
transmittance for standard illuminant D65 [%] :		$\tau_V = 62,7$
reflectance for standard illuminant D65 [%] (*):		$\rho_V = 14,4$
reflectance for standard illuminant D65 [%] (**):		$\rho'_V = 17,4$
general colour rendering index [%] :		$R_a = 94,7$
energy :		
solar direct transmittance [%] :		$\tau_e = 31,8$
solar direct reflectance [%] (*):		$\rho_e = 37,4$
solar direct reflectance [%] (**):		$\rho'_e = 43,6$
solar direct absorption [%] (*):		$a = 30,8$
secondary internal heat transfer factor [%] (*):		$q_i = 2,0$
total solar energy transmittance (solar factor) [%] (*):		$g = 33,8$
shading coefficient (=g/0,87) (*):		$sc = 0,39$
thermal conductance (U-value) [W/m ² K] (EN 673):		$U_g = 1,0$
slope [°] : $\alpha=90,0$		
(*) incident radiation from the outside		
(**) incident radiation from the inside		

The calculated values are for orientation only and do not offer any guarantee regarding the fabrication of the un- intended end- product.

Glass configurations do not amount to a guarantee of product availability.