

calculation in accordance to EN 410

002

Glazing from outside to inside

18.00 mm

| | | |
|--------------------|-------------------------------|---|
| pane1 | substrate | Guardian Float Glass ExtraClear, 4.00 mm |
| spacer/gas1 | | 10 mm / air 10%, argon 90% |
| pane2 | coating on pos.3 substrate | Guardian ClimaGuard Premium Guardian Float Glass ExtraClear, 4.00 mm |

Results

UV :

transmittance [%] : $\tau_{UV} = 35,0$

light :

transmittance for standard illuminant D65 [%] : $\tau_V = 80,1$

reflectance for standard illuminant D65 [%] (*): $\rho_V = 12,2$

reflectance for standard illuminant D65 [%] (**): $\rho_V = 12,3$

general colour rendering index [%] : $R_a = 97,4$

energy :

solar direct transmittance [%] : $\tau_e = 54,5$

solar direct reflectance [%] (*): $\rho_e = 28,8$

solar direct reflectance [%] (**): $\rho_e = 27,8$

solar direct absorption [%] (*): $a = 16,7$

secondary internal heat transfer factor [%] (*): $q_i = 8,1$

total solar energy transmittance (solar factor) [%] (*): $g = 62,6$

shading coefficient (=g/0,87) (*): $sc = 0,72$

thermal conductance (U-value) [W/m²K] (EN 673): $U_g = 1,5$
slope [°]: $\alpha = 90,0$

(*) incident radiation from the outside

(**) incident radiation from the inside

The calculated values are for orientation only and do not offer any guarantee regarding the fabrication of the un- intended end- product.

Glass configurations do not amount to a guarantee of product availability.