

calculation in accordance to EN 410

date : 17.02.2012  
database version : 10.03.2011 / K  
version : 3.0

029

## Glazing from outside to inside

18.00 mm

<b>pane1</b>	substrate	Guardian Float Glass ExtraClear, 4.00 mm
<b>spacer/gas1</b>		10 mm / air 10%, crypton 90%
<b>pane2</b>	coating on pos.3	Guardian ClimaGuard 1.0
	substrate	Guardian Float Glass ExtraClear, 4.00 mm

## Results

### **UV :**

transmittance [%] :  $\tau_{UV} = 26,5$

### **light :**

transmittance for standard illuminant D65 [%] :  $\tau_V = 70,1$

reflectance for standard illuminant D65 [%] (\*):  $\rho_V = 20,2$

reflectance for standard illuminant D65 [%] (\*\*):  $\rho_V = 22,6$

general colour rendering index [%] :  $R_a = 97,6$

### **energy :**

solar direct transmittance [%] :  $\tau_e = 44,7$

solar direct reflectance [%] (\*):  $\rho_e = 38,4$

solar direct reflectance [%] (\*\*):  $\rho_e = 40,3$

solar direct absorption [%] (\*):  $a = 16,9$

secondary internal heat transfer factor [%] (\*):  $q_i = 8,2$

total solar energy transmittance (solar factor) [%] (\*):  $g = 52,8$

shading coefficient (=g/0,87) (\*):  $sc = 0,61$

thermal conductance (U-value) [W/m<sup>2</sup>K] (EN 673):  $U_g = 1,0$   
slope [°]:  $\alpha = 90,0$

(\*) incident radiation from the outside

(\*\*) incident radiation from the inside

**The calculated values are for orientation only and do not offer any guarantee regarding the fabrication of the un- intended end- product.**

**Glass configurations do not amount to a guarantee of product availability.**