

calculation in accordance to EN 410

031

**Glazing from outside to inside**      26.00 mm

<b>pane1</b>	substrate	Guardian Float Glass ExtraClear, 6.00 mm
	coating on pos.2	Guardian SunGuard HS SuperNeutral 70/41
<b>spacer/gas1</b>		16 mm / air 10%, argon 90%
<b>pane2</b>	substrate	Guardian Float Glass ExtraClear, 4.00 mm

**Results**

<b>UV :</b>		
transmittance [%] :		$\tau_{UV} = 25,9$
<b>light :</b>		
transmittance for standard illuminant D65 [%] :		$\tau_V = 69,9$
reflectance for standard illuminant D65 [%] (*):		$\rho_V = 10,7$
reflectance for standard illuminant D65 [%] (**):		$\rho'_V = 11,6$
general colour rendering index [%] :		$R_a = 96,2$
<b>energy :</b>		
solar direct transmittance [%] :		$\tau_e = 38,7$
solar direct reflectance [%] (*):		$\rho_e = 33,5$
solar direct reflectance [%] (**):		$\rho'_e = 37,4$
solar direct absorption [%] (*):		$a = 27,8$
secondary internal heat transfer factor [%] (*):		$q_i = 2,3$
total solar energy transmittance (solar factor) [%] (*):		$g = 41,0$
shading coefficient (=g/0,87) (*):		$sc = 0,47$
thermal conductance (U-value) [W/m <sup>2</sup> K] (EN 673):		$U_g = 1,1$
slope [°] : $\alpha=90,0$		
(*) incident radiation from the outside		
(**) incident radiation from the inside		

**The calculated values are for orientation only and do not offer any guarantee regarding the fabrication of the un- intended end- product.**

**Glass configurations do not amount to a guarantee of product availability.**